



Report for: Viewmax Windows and Doors Ltd.
23 McCleary Crt. Unit # 2
CONCORD, Ontario
L4K 3R6

Laboratory No. 874790-21

Report Date: November 03, 2021
Received Date: November 02, 2021

Attention: Nenad Lihtar

Specimen: Steel Profile, 120mm x 50mm x 2.5mm thick, identified as VM12050

LONGITUDINAL TENSILE TEST REPORT


	<u>RESULT</u>
Specimen Width:	12.57 mm
Specimen Thickness:	2.52 mm
Yield Strength (0.2% Offset):	404 MPa
Ultimate Tensile Strength:	491 MPa
Elongation in 50.0 mm:	16 %

Testing performed according to ASTM A370-20.

Page 1 of 1

This report is subject to the following terms and conditions: 1. This report relates only to the specimen provided and there is no representation or warranty that it applies to similar substances or materials or the bulk of which the specimen is a part. 2. The content of this report is for the information of the customer identified above only and it shall not be reprinted, published or disclosed to any other party except in full. Prior written consent from Cambridge Materials Testing Limited is required. 3. The name Cambridge Materials Testing Limited shall not be used in connection with the specimen reported on or any substance or materials similar to that specimen without the prior written consent of Cambridge Materials Testing Limited. 4. Neither Cambridge Materials Testing Limited nor any of its employees shall be responsible or held liable for any claims, loss or damages arising in consequence of reliance on this report or any default, error or omission in its preparation or the tests conducted. 5. Specimens are retained 6 months, test reports and test data are retained 7 years from date of final test report and then disposed of, unless instructed otherwise in writing. 6. When making a statement of conformity to a specification or standard the report will make the statement of conformity based on the absolute value of the test result. Test Report Template Revision January 14, 2019

Cambridge Materials Testing Limited

Per	 Nicholas Wolfenberg	Authorized By
Per	 Reghan Hopper	Technician